



## CEMCOTE

*an integrally colored cementitious surface coating*

---

### DESCRIPTION

Cemcote is an integrally colored cement based exterior coating designed to correct color variations in colored stucco resulting from uneven drying, rain outs, cold joints, stains and patching.

Cemcote can also be used to change or renew existing stucco surfaces including ornamental block.

### COMPONENTS

Cemcote is made up of a factory blended combination of white Portland cement, extra fine marble.

Colored pigmented oxides and other chemical components. All components in the manufacturing of Cemcote meet or exceed ASTM specifications.

### USES

Cemcote is not a paint but rather a cementitious coating which becomes an integral part of the cementitious surface being coated. Cemcote provides a hard, durable surface with excellent adhesion to both damp and dry masonry surfaces. It is easily blended and provides a long lasting colored surface coating. Cemcote permits the natural "breathing" of masonry structures.

### INSTALLATION

#### Surface Preparation

Masonry surfaces to be coated should be free of paint, excess mortar, any loose particles, iron, steel or other foreign materials which may prevent proper bonding to the existing surfaces. Spots or stains should be removed with a solution of 10% to 30% muriatic acid. Oil or grease should be removed with a suitable caustic solution or cleaning compound. After cleaning, surfaces must be rinsed thoroughly with water to remove all traces of acid or cleaning solutions.

Slick or non-porous areas of concrete should be etched with a 10% to 30% solution of muriatic acid and then washed clean. Repeat this operation if necessary until surface is free of slick spots.

### MIXING

Add clean potable water only. Measure equal amounts of water for each batch to ensure color uniformity, and mix each batch for the same length of time.

Mix only enough Cemcote that can be used in 30 minutes. For best results, try to use Cemcote as soon as possible after it has been mixed. Any addition of other materials could be harmful to the finished product. Keep tools and equipment clean.

Mix approximately 4-1/2 gallons of water per 40 pound bag of Cemcote. Place 1/3 of the water (approximately 1-1/2 gallons per bag) and all of the Cemcote in the mixing receptacle. Blend to a smooth lump-free consistency. Let stand for 10 minutes. Then add 3 pints of PLEX-33 per bag of Cemcote and the remainder of the water, and mix thoroughly.

### APPLICATION

Cemcote is a complete product. Any addition of materials (other than those specified or recommended by Premix-Marbletite Manufacturing Co.) could be harmful to the performance of the finished product. Do not apply in temperatures lower than 55°F or greater than 90°F. Cemcote does not possess any filling capabilities, therefore, it cannot change the structural value of the surface to which it is applied. The resulting appearance of cemcote as with any other non-aggregated coating, is subject to the physical uniformity of the substrate.

**CEMCOTE IS NOT A WATERPROOFING PRODUCT.**

The effectiveness of this product depends upon its proper application, and the condition and preparation of the surface to which it is applied.

Apply cemcote with a stiff brush (Calcimine-type brush), roller (2-1/4" diameter with 1" nap) or spray equipment. Generally work shorter areas than if painting. Always roll in an upwards direction after clipping roller in material and work equal areas with each roller refill. Try to leave uniform amounts of material on each square foot of wall surface. Cemcote works best over trowel texture finishes. Float finishes may require Cemcote be brush applied. Spray finishes may require 2 coats of Cemcote. When Cemcote is roller applied avoid overlaps or roller end runs. Roll, brush or spray both horizontally and vertically while Cemcote is still wet for best results.

Cemcote should be applied in good weather and should dry in one hour or less under normal conditions.

### SPECIAL NOTE

Due to job conditions and base variations, standard colors supplied may require adjustment. Test matching 4 days prior to main work is recommended. The day that the Cemcote is applied, the color should appear a little light. The color will darken slightly the first week.



## **CEMCOTE**

*an integrally colored cementitious surface coating*

---

### **LIMITED WARRANTY**

The product shall be in its unopened package, of the kind specified within. There is no other warranty or representation of any kind, express or implied (including no warranty of merchantability or of fitness for a particular purpose). No warranty shall be implied by law.

This Limited Warranty continues only until such time as the buyer opens the package and examines its contents.

If the buyer, after opening the package and examining its contents, determines that the product is not of the kind specified herein, the buyer should write to Premix-Marbletite Manufacturing Company, 1259 N.W. 21st Street, Pompano Beach, Florida 33069 explaining the defect and enclosing a sample of the product. Premix-Marbletite, upon receipt of the sample from the buyer and without cost to the buyer, will replace the portion of the product that is determined to be defective. This shall be the buyer's sole remedy for breach of warranty and such remedy shall be in lieu of any claim for damages, including consequential damages.

Some States do not allow limitations on how long an implied warranty lasts, or exclusions or limitations of incidental or consequential damages, so the above limitations or exclusions may not apply to you. This warranty gives you specific legal rights, and you may also have other rights which vary from State to State.

### **COLOR VARIATION IS NOT A WARRANTABLE ITEM**

### **MAINTENANCE**

Occasional water pressure cleaning of between 500 and 1,000 p.s.i. should produce satisfactory results. Specific information as to the removal of stains of foreign materials, or instructions for patching or repairing can be obtained from the corporate office.

### **TECHNICAL**

Factory trained, experienced representatives are available to answer questions and assist with recommendations.

Technical information is also available from the executive offices.

**PREMIX-MARBLETITE MFG. CO.**

**1259 NW 21st STREET • POMPANO BEACH, FL. 33069**  
**954/917.7665 • fx: 954/917.2775 • 800/432.5097**

**PREMIX-MARBLETITE MFG. CO.**

**325 OLD SANFORD OVIEDO ROAD • WINTER SPRINGS, FL. 32708**  
**407/327.0830 • fx: 407/327.8942 • 800/432.5097**